

**GRAPHICS** - INK-JET DIGITAL

Issue date : 24/03/2016 Date last modification : 30/04/2018

# 4-GL2A-09782 RI-JET DECO-WALL 100 HOP AP972 EXTRA PERMANENT WK135

# Face Material

High opacity matt white monomeric vinyl film.

Type Colour and Finish Weight Thickness Monomeric vinyl Matt white 134 g/m<sup>2</sup> ±10% ISO-536 100 µ ±10% ISO 534-80 1 % ±10%

## Adhesive

Extra permanent solvent based adhesive with excellent adhesion on indoor and outdoor walls.

Reference Type Min. Appl. Temp. Service Temp. Shear Tack Final Adhesion AP927 extra permanent Acrylic extra permanent +5°C -30°C / +120°C Medium 12 N/inch<sup>2</sup> 16 N/inch

#### Liner

Туре	One side siliconised clay coated	
Colour and Finish	Kraft	
Colour and Finish	White	
Weight	135 g/m²	PP-032 - ISO
-	±10%	536
Thickness	145 µ ±10%	ISO 534
Transparency	n.a. %	DIN 53 147-64

#### **Applications**

For walls interior decoration.

This PVC self adhesive material offers a cost effective solution to interior designer who are looking for a film to decorate internal walls or shop interior. We advise an overlap of 1,5 cm when positioning the

decals. Indoor durability 4 years unprinted material. If the printing solvents aren't completely removed before

installation the resultant graphic will show very high shrinkage and edge curl. The shrinkage of the unprinted material, based on the Finat

# test method FTM 14, give us values <2%.

#### Printing Methods

Printable with eco-solvent, solvent, UV and Latex ink-jet. Print and immediate cut is feasible.

Testing for suitability between media, printers and inks is always recommended prior to use.

### Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of  $\ 22^\circ\text{C} \pm 2^\circ\text{C}$  and 50  $\pm$  5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.



Ritrama S.p.A. Via Senatore Simonetta, 24 20867 Caponago (MB) ITALY e-mail:info@ritrama.com w w w . r i t r a m a . c o m

