

DTEC MURAL DECO TEX SA MATT

**Description:**

*Soft Monometric PVC film*

*Color: Transparent*

*Surface: Matt*

**Release Liner:**

*140±10gsm PE-Coated silicon paper*

**Adhesive:**

*Solvent polyacrylate, Permanent, Transparent.*

**Technical data:**

<i>Characteristics</i>	<i>Avarage Values</i>
<b>Thickness (without protective paper and adhesive)</b>	<i>100±10 microns monomeric PVC film.</i>
<b>Dimensional stability (FINAT TM14)</b>	<i>Adhered to steel, No shrinkage in cross direction, in length 0.50mm max</i>
<b>Dimensional stability (FINAT TM14)</b>	<i>Adhered to aluminum. -20°C to +60°C, no variation.</i>
<b>Adhesive</b>	<i>Solvent polyacrylate Permanent adhesive</i>
<b>Seawater resistance (DIN 50021)</b>	<i>Adhered to aluminum, after 48h/23°C no variation.</i>
<b>Adhesive Power (FINAT TM 1, after 24h, stainless steel)</b>	<i>16±2N/25 mm</i>
<b>Tensile strength (ASTM D882-02; 200mm/Min) along across</b>	<i>min.22 MPa min.18 MPa</i>
<b>Elongation at break (ASTM D882-02; 200mm/Min) along across</b>	<i>min 200% min 150%</i>
<b>Shelf life</b>	<i>Up to 1 year</i>
<b>Application temperature</b>	<i>min. +10°C</i>
<b>Service life by specialist application Under vertical outdoor exposure (normal climate of China)</b>	<i>Up to 1 year</i>
<b>Slip resistance (oil-wet ramp test)</b>	<i>R9 *Critical angle of inclination:9.60</i>

*Attention:*

*After printing the ink must be thoroughly dry in order to avoid any affect on the later combination with the laminate. Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material.*

*The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.*

