

# dtec Banner Classic Frontlit Matt 440gsm

## PRODUCT SPECIFICATION:

### 1. General Properties:

<i>ITEM</i>	<i>DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>Fabric</i>	<i>High tenacity yarns 100%PES(300D*500D)</i>		<i>DIN EN ISO2060</i>
<i>Construction</i>	<i>Knitting 18*12</i>	<i>inch</i>	<i>DIN60001</i>
<i>Total weight</i>	<i>440</i>	<i>g/m<sup>2</sup></i>	<i>DIN53352 BS3424 method5A</i>
<i>Weight of fabric</i>	<i>55</i>	<i>g/m<sup>2</sup></i>	<i>DIN53352 BS3424 method5B</i>
<i>Weight of pvc coating</i>	<i>385</i>	<i>g/m<sup>2</sup></i>	<i>DIN53352 BS3424 method5B</i>
<i>Tensile strength</i>	<i>Warp :635</i>	<i>N/5cm</i>	<i>DIN53354 BS3424 method6A</i>
	<i>Weft :450</i>		
<i>Tearing strength</i>	<i>Warp :125</i>	<i>N</i>	<i>DIN53356 BS3424 method 7A</i>
	<i>Weft :110</i>		
<i>Adhesion</i>	<i>60</i>	<i>N/5cm</i>	<i>DIN53357 BS3425 method9B</i>
<i>Suitable temperature</i>	<i>-20 -----+70</i>	<i>°C</i>	<i>DIN 53372 BS3424 method10</i>
<i>Flame retardancy</i>	<i>No</i>		
<i>Lacquering</i>	<i>No</i>		

*The indexes above are on average, so there will be ±5% tolerance of actual indexes*



**Ecco Plus Sp. z o.o.**  
ul. Sienkiewicza 1/1 lok. 102  
15-092 Białystok  
tel./faks 85 747 94 11  
[www.eccoplus.pl](http://www.eccoplus.pl)



**Ecco Plus Sp. z o.o.**  
*ul. Sienkiewicza 1/1 lok. 102*  
*15-092 Białystok*  
*tel./faks 85 747 94 11*  
[www.eccoplus.pl](http://www.eccoplus.pl)