

dtec Banner Plus Frontlit Matt 450gsm

PRODUCT SPECIFICATION:

1. General Properties

<i>ITEM</i>	<i>DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<i>Fabric</i>	<i>High tenacity yarns 100%PES(1000D)</i>		<i>DIN EN ISO2060</i>
<i>Construction</i>	<i>Weaving 18*18</i>	<i>inch</i>	<i>DIN60001</i>
<i>Total weight</i>	<i>450</i>	<i>g/m²</i>	<i>DIN53352 BS3424 method5A</i>
<i>Weight of fabric</i>	<i>155</i>	<i>g/m²</i>	<i>DIN53352 BS3424 method5B</i>
<i>Weight of pvc coating</i>	<i>295</i>	<i>g/m²</i>	<i>DIN53352 BS3424 method5B</i>
<i>Tensile strength</i>	<i>Warp :2200</i>	<i>N/5cm</i>	<i>DIN53354 BS3424 method6A</i>
	<i>Weft :1900</i>		
<i>Tearing strength</i>	<i>Warp :300</i>	<i>N</i>	<i>DIN53356 BS3424 method 7A</i>
	<i>Weft :250</i>		
<i>Adhesion</i>	<i>80</i>	<i>N/5cm</i>	<i>DIN53357 BS3425 method9B</i>
<i>Suitable temperature</i>	<i>-20 -----+70</i>	<i>°C</i>	<i>DIN 53372 BS3424 method10</i>
<i>Flame retardancy</i>	<i>No</i>		
<i>Lacquering</i>	<i>No</i>		

The indexes above are on average, so there will be ±5% tolerance of actual indexes



Ecco Plus Sp. z o.o.
ul. Sienkiewicza 1/1 lok. 102
15-092 Białystok
tel./faks 85 747 94 11
www.eccoplus.pl



Ecco Plus Sp. z o.o.
ul. Sienkiewicza 1/1 lok. 102
15-092 Białystok
tel./faks 85 747 94 11
www.eccoplus.pl